



NITRILE EXAMINATION GLOVE

Powder Free Nitrile Examination Glove

For those concerns about latex allergies, the basic Nitrile Examination Glove provides a cost effective solution to encounter the problems. With our advance formulation, our Powder Free Nitrile Examination Gloves are also soft, smooth and comfortable to wear. It provides the feel of natural rubber gloves although it is latex free. There is no DEHP as found in Vinyl Gloves. For those dislike the powder, this will be the perfect solution. You can always expect the best from Ascent Care.



GLOVE ATTRIBUTE

| GLOVE ATTRIBUTE | | |
|----------------------------------------------|------------------------------------------------------|----------------------|
| Material | High Grade Nitrile Butadiene Rubber (NBR) | |
| Type | NITRILE Examination Glove, Non Sterile, Ambidextrous | |
| Color | Blue, Beige or Purple | |
| Sizes Available | X-Small, Small, Medium, Large, X-Large | |
| Cuff | Beaded | |
| Application | Medical Activities except surgery | |
| Packaging | 100 gloves by weight per box, 10 boxes per case | |
| Surface Finishing | Finger textured or palm textured | |
| Product Conformance | Conforms to ASTM 3578 and EN 455 standards | |
| Allergenic & Skin Sensitization Test Results | Primary Skin Irritation | NON-Primary Irritant |
| | Sensitization (BUEHLER) | NON-SENSITIZING |

Our Advantages :

- ✓ Excellent tactile sensitivity for precise handling.
- ✓ Superior Tensile Strength.
- ✓ 100% latex free eliminates potential allergic reactions to natural protein.
- ✓ Excellent fit, feel and odorless.
- ✓ Specially treated textured surface allow reliable grip in wet and dry conditions.
- ✓ Superior punctures and tears resistance properties.



GLOVE PROFILE

| Glove Profile | | | |
|---------------------|-------------------------|-----------------|-------------------------|
| Dimension | Glove Size | Palm Width (mm) | Normal Length (mm) |
| | X-Small | 77 ± 3 | ≥ 242 ± 2 |
| | Small | 85 ± 3 | ≥ 242 ± 2 |
| | Medium | 95 ± 3 | ≥ 242 ± 2 |
| | Large | 105 ± 3 | ≥ 242 ± 2 |
| | X-Large | 111 ± 3 | ≥ 242 ± 2 |
| Thickness | Point of measurement | | ASTM - Single Wall (mm) |
| | Cuff | | min 0.05 |
| | Palm | | min 0.05 |
| Physical Properties | Tensile Strength | | ASTM |
| | Before aging (MPa) | | min 14.0 |
| | After aging (MPa) | | min 14.0 |
| | Elasticity / Elongation | | ASTM |
| | Before aging | | min 650% |